

# GARGO INTERNATIONAL

An ISO 9001:2008 Certified Co.

Manufactures of Adrol Lubricants and Creases Steel Grip Conveyor Belts, Transmission Rubber Belts

### **ADROL MP-3 GREASE**

### MULTIPURPOSE CALCIUM GREASE

#### **DESCRIPTION**

**ADROL MP-3 GREASE** - Multipurpose Calcium Grease are smooth structured, creamish white coloured soap grease. These Grease possess good water resistance characteristics and can be used for lubricants of machine elements operating in conditions where water ingress cannot be avoided. Recommended widely for plain bearings operating under moderate to low temperature 0°C To -60°C.

#### **APPLICATION**

Recommended for all classes of service in automotive lubrication. Meets IS: 12203: 1999 (Re-affirmed 2004)

#### **PERFORMANCE BENEFITS**

- Perform satisfactorily even in wet condition since they posses superior water resistance quality.
- Possess excellent quality.
- Possess excellent shear stability.
- Provide ease of application by manual lubrication equipment, since they have excellent dispensing property.

DISCLAIMER: "This message is intended only for the use of the addressee and may contain information that is privileged, confidential and exempt from disclosure under applicable law. If the reader of this message is not the intended recipient, or the employee or agent responsible for delivering the message to the intended recipient, you are hereby notified that any dissemination, distribution or copying of this communication is strictly prohibited. If you have received this e-mail in error, please notify us immediately by return e-mail and delete this e-mail and all attachments from your system."





## GARGO INTERNATIONAL An ISO 9001:2008 Certified Co.

Manufactures of Adrol Lubricants and Creases Steel Grip Conveyor Belts, Transmission Rubber Belts

### **TYPICAL PROPERTIES**

CHARACTERISTICS	SPECIFICATIONS
Appearance	Smooth & Slightly Fibrous
Consistency of the Grease, @25 ± 0.5 °C,0.1mm units UN Worked	Shall not differ from worked 60 X more than 10 units
Worked 60 X	220-250
Worked 100,000 X	Shall not differ from worked 60 X more than 30 units
Drop point, min, °C	90
Free Alkalinity, as LiOH, % wt, Max	0.1
Free Organic Acidity, as, Oleic Acid, % wt	NIL
Heat Stability, @100°C for 30hrs, % wt Oil Separated, Max	5

<sup>\*</sup>Test results are based on samples.



DISCLAIMER: "This message is intended only for the use of the addressee and may contain information that is privileged, confidential and exempt from disclosure under applicable law. If the reader of this message is not the intended recipient, or the employee or agent responsible for delivering the message to the intended recipient, you are hereby notified that any dissemination, distribution or copying of this communication is strictly prohibited. If you have received this e-mail in error, please notify us immediately by return e-mail and delete this e-mail and all attachments from your system."

